

Engineered 1/2" x 7 1/2" platform



Product Technical Specifications

Nature of material	Top layer: Hardwood, nominal 3 mm thick Base: Plywood
Dimensions	Thickness: 1/2" (13 mm) Width: 7 1/2" (190 mm) Lengths: Random, from 23" to 75" (584,2 mm to 1 900 mm)
Profiling	Micro v-joint on 4 sides
Moisture content	Between 6% and 9%
Species and Janka hardness (lb)	White Oak (1 360)
Available grades	Distinction and Authentic
Colors	Orion, Nova, Celeste, Starlight, Lyra, Equinox, Solaris, Aurora
Accessories	Reducers and Stair nosings Touch-up kits, Maintenance kit
Manufacturing	Designed, stained and finished in Canada by Mercier Wood Flooring (imported platform)

Finish and Warranties



Mercier Generations+ Finish

Acrylate polymer-based finish consisting of plant-based oil and UV-cured polymer and reinforced with suspended aluminum oxide particles.

Available gloss: Matte-brushed (10°)

Warranties

35 years for normal residential use
5 years for light commercial use
Structural lifetime warranty

Non-yellowing: The non-yellowing formula in the finishes reduces the natural wood board yellowing process.

Antimicrobial: The antimicrobial contained in our finishes helps reduce the risk of spreading bacteria and mildew. Completely non-toxic, this special treatment adds an additional level of protection for healthier floors.

Packaging	Number of boxes	Content	Width	Length	Height	Weight
Box		35,16 sq. ft.	8 1/4"	79"	5"	59 lb
Pallet	35	1230,6 sq. ft.	42"	79"	38"	2 000 to 2 100 lb

Engineered 1/2" x 7 1/2" platform

Installation

Types of installation	Nailed, Glued, Stapled or Floating
Relative humidity	Between 35% and 55%
Subfloor	<ul style="list-style-type: none"> • OSB or 3/4" (19 mm) plywood Joists spaced no more than 19" (48,3 cm) C-C • 5/8" (16 mm) plywood Joists spaced no more than 16" (40,6 cm) C-C • Concrete slab
Installation sites	Basement, first floor and upper floors
Radiant heated floor	Yes. Refer to the Technical bulletin #5 for more details.

VOC / Formaldehyde

VOC-free and formaldehyde-free finish: ASTM D-5116

Greenguard Gold certification: Applies to all species, widths and colors.

Phtalate-free finish: OSHA method 104

TSCA Title VI compliant & CANFER compliant

Maximum Greenguard Gold emission criteria

TVOC	≤ 0,22 mg/m ³
Formaldehyde	≤ 0,0073 ppm
Total Aldehydes	≤ 0,043 ppm
IVOCs	≤ 1/100 TLV and 1/2 chronic REL

Applicable standards

Surface burning ASTM-E-84	Class C (varies according to the wood species) Flame Spread Index: 100 to 150 Smoke Development: 75 to 400 according to the wood species
Surface burning CAN/ ULC-S102.2	Flame Spread Index (FSR): 130 Smoke Development (SDC): 255
Abrasion resistant finish (Taber test)	Mercier Generations+ finish: Nema LD3: 1 000 cycles
Static friction coefficient ASTM D2394	Mercier Generations+ finish: Matte-brushed: 0,68

Certifications



The information in this document was accurate at the time of publication. Mercier Wood Flooring reserves the right to change the products or products characteristics at any time without notice.