

## **Technical Specifications**

## Solid 3/4" x 3 1/4" platform



### **Product Technical Specifications.**

| Nature of material                 | 100% Hardwood  |
|------------------------------------|--|
| Dimensions                         | Thickness: 3/4" (19 mm) Width: 3 1/4" (83 mm) Lengths: Random, from 12" to 84" (305 mm to 2 134 mm)                              |
| Profiling                          | Micro v-joint on 4 sides   |
| Moisture content                   | Between 6% and 9%  |
| Species and<br>Janka hardness (lb) | White Oak (1 360), Red Oak (1 290), Hard Maple (1 450),<br>White Ash (1 320), Hickory (1 820), Yellow Birch (1 260)              |
| Available grades                   | Select & Better, Distinction and Authentic   |
| Colors                             | Refer to the current Mercier Product Chart   |
| Accessories                        | T-Moldings, Quarter Rounds, Thresholds, Reducers and Stair nosings, according to the wood species Touch-up kits, Maintenance kit |

#### **Finishes and Warranties**



#### **Mercier Generations Finish**

Acrylate polymer-based finish consisting of plant-based oil and UV-cured polymer and reinforced with suspended aluminum oxide particles.



### Warranties

35 years for normal residential use 5 years for light commercial use Structural lifetime warranty



#### **Generations Intact 2500 Finish**

Finish composed of plant-based oil and microfragmented aluminum particles ( ${\rm AL_2O_3}$ ) in suspension in a UV-cured polyurethane resin.

Available gloss: Intact (10°)

#### Warranties

50 years for normal residential use 10 years for light commercial use 3 years for commercial use with direct outdoor access Structural lifetime warranty

**Non-yellowing:** The non-yellowing formula in the finishes reduces the natural wood board yellowing process.

**Antimicrobial:** The antimicrobial contained in our finishes helps reduce the risk of spreading bacteria and mildew. Completely non-toxic, this special treatment adds an additional level of protection for healthier floors.

| Packaging | Number of boxes | Content                        | Width | Length | Height | Weight                              |
|-----------|-----------------|--------------------------------|-------|--------|--------|-------------------------------------|
| Box       |                 | 22 sq. ft. (2 m <sup>2</sup> ) | 10"   | 87"    | 3 1/4" | 60 lb (27 kg)                       |
| Pallet    | 40              | 880 sq. ft. (81,8 m²)          | 42"   | 87"    | 36"    | 2 200 to 3 000 lb (998 to 1 361 kg) |



# **Technical Specifications**

## Solid 3/4" x 3 1/4" platform

## Installation \_\_\_\_\_

| Types of installation | Nailed or Stapled   |  |
|-----------------------|---|--|
| Relative humidity     | Between 35% and 55%   |  |
| Subfloor              | <ul> <li>OSB or 3/4" (19 mm) plywood Joists spaced no more than 19" (48,3 cm) C-C</li> <li>5/8" (16 mm) plywood Joists spaced no more than 16" (40,6 cm) C-C</li> </ul> |  |
| Installation sites    | First floor and upper floors  |  |
| Radiant heated floor  | No. Refer to the Technical bulletin #5 for more details.  |  |

## VOC / Formaldehyde\_\_\_\_\_

**VOC-free and formaldehyde-free finish:** ASTM D-5116

**Greenguard Gold certification:** Applies to all species,

widths and colors.

Phtalate-free finish: OSHA method 104

### **Maximum Greenguard Gold emission criteria**

| TVOC            | ≤ 0,22 mg/m <sup>3</sup>      |
|-----------------|-------------------------------|
| Formaldehyde    | ≤0,0073 ppm                   |
| Total Aldehydes | ≤ 0,043 ppm                   |
| IVOCs           | ≤ 1/100 TLV and ½ chronic REL |

## Applicable standards\_\_\_\_\_

| Surface burning<br>ASTM-E-84           | Class C (varies according to the wood species) Flame Spread Index: 100 to 150 Smoke Development: 75 to 400 according to the wood species    |
|--|---|
| Surface burning CAN/<br>ULC-S102.2     | Flame Spread Index (FSR): 130<br>Smoke Development (SDC): 255   |
| Abrasion resistant finish (Taber test) | Mercier Generations finish: Nema LD3: 1 000 cycles<br>Generations Intact 2500 finish: Nema LD3: 2 500 cycles                                |
| Static friction coefficient ASTM D2394 | Mercier Generations finish (according to the gloss) Satin: 0,57   Matte and Matte-brushed: 0,68 Generations Intact 2500 finish Intact: 0,56 |

### Certifications \_\_\_\_\_





The information in this document was accurate at the time of publication. Mercier Wood Flooring reserves the right to change the products or products characteristics at any time without notice.