

Technical Specifications

Engineered 1/2" x 5" platform





Product Technical Specifications ____

Nature of material	Top layer: Hardwood, 4 mm thick Base: 7-ply crossed hardwood plywood			
Dimensions	Thickness: 1/2" (12,7 mm) Width: 5" (127 mm) Lengths: Random, from 12" to 83" (305 mm to 2 108 mm)			
Profiling	Micro v-joint on 4 sides			
Moisture content	Between 6% and 9%			
Species and Janka hardness (lb)	White Oak (1 360), Red Oak (1 290), Hard Maple (1 450), Hickory (1 820), White Ash (1320)			
Available grades	Select & Better, Distinction and Authentic			
Colors	Refer to the current Mercier Product Chart			
Accessories	T-Moldings, Quarter Rounds, Thresholds, Reducers, Stair nosings, Vents Touch-up kits, Maintenance kit			

Finishes and Warranties



Mercier Generations Finish

Acrylate polymer-based finish consisting of plant-based oil and UV-cured polyurethane and reinforced with suspended aluminum oxide particles.



Warranties

35 years for normal residential use 5 years for light commercial use Structural lifetime warranty



Generations Intact 2500 Finish

Finish composed of plant-based oil and microfragmented aluminum particles (${\rm AL_2O_3}$) in suspension in a UV-cured polyurethane resin.

Available gloss: Intact (10°)

Warranties

50 years for normal residential use 10 years for light commercial use 3 years for commercial use with direct outdoor access Structural lifetime warranty

Non-yellowing: The non-yellowing formula in the finishes reduces the natural wood board yellowing process.

Antimicrobial: The antimicrobial contained in our finishes helps reduce the risk of spreading bacteria and mildew. Completely non-toxic, this special treatment adds an additional level of protection for healthier floors.

Packaging	Number of boxes	Content	Width	Length	Height	Weight
Box		33 sq. ft. (3,1 m ²)	10"	87"	3 1/4"	62 lb (28 kg)
Pallet	40	1 320 sq. ft. (123 m²)	42"	87"	36"	2 700 to 3 000 lb (1 225 to 1 361 kg)



Technical Specifications

Engineered 1/2" x 5" platform

Installation _____

Types of installation	Nailed, Glued, Stapled or Floating* (*Except Hickory)		
Relative humidity	Between 30% and 65%		
Subfloor	 OSB or 3/4" (19 mm) plywood Joists spaced no more than 19" (48,3 cm) C-C 5/8" (16 mm) plywood Joists spaced no more than 16" (40,6 cm) C-C Concrete slab 		
Installation sites	Basement, first floor and upper floorss		
Radiant heated floor	Yes. Refer to the Technical bulletin #5 for more details.		

VOC / Formaldehyde _____

VOC-free and formaldehyde-free finish: ASTM D-5116

Greenguard Gold certification: Applies to all species, widths and colors.

Phtalate-free finish: OSHA method 104

EPA TSCA Title VI compliant

Maximum Greenguard Gold emission criteria

TVOC	≤ 0,22 mg/m ³
Formaldehyde	≤0,0073 ppm
Total Aldehydes	≤ 0,043 ppm
IVOCs	≤ 1/100 TLV and ½ chronic REL

Applicable standards_

Surface burning ASTM-E-84	Class C (varies according to the wood species) Flame Spread Index: 100 to 150 Smoke Development: 75 to 400 according to the wood species		
Surface burning CAN/ ULC-S102.2	Flame Spread Index (FSR): 130 Smoke Development (SDC): 255		
Abrasion resistant finish (Taber test)	Mercier Generations finish: Nema LD3: 1 000 cycles Generations Intact 2500 finish: Nema LD3: 2 500 cycles		
Static friction coefficient ASTM D2394	Mercier Generations finish (according to the gloss) Satin: 0,57 Matte and Matte-brushed: 0,68 Generations Intact 2500 finish Intact: 0.56		

Certifications ____





The information in this document was accurate at the time of publication. Mercier Wood Flooring reserves the right to change the products or products characteristics at any time without notice.